

Opening New Frontiers in Singlet Fission Research







Remco W. A. Havenith

Stratingh Institute for Chemistry, Zernike Institute for Advanced Materials, University of Groningen, The Netherlands

Ghent Quantum Chemistry Group, Ghent University, Belgium







Who contributed









Ria Broer



Luis Enrique



Kathir









Coen de Graaf





Tjerk Straatsma



university of groningen


faculty of science and engineering


stratingh institute for chemistry

FOM Focus Group Groningen 'Next Generation Organic Photovoltaics'

- Aim:
 - Deliver the science for highly efficient, long-lived, and lowcost organic photovoltaic devices
- Challenge:
 - Charge separation at the donor/acceptor interface
- Approach:
 - Multi-disciplinary:
 - Material development
 - Physical characterisation (OPV device physics)
 - Theoretical modelling









Theoretical challenges


- Predict molecular properties that determine the dielectric properties of the interface
 - Dipole moments
 - Polarisability
- Modelling of the donor/acceptor interface
 - Molecular Dynamics simulations
 - Time scales of molecular motion
- Calculation of the excited states
 - Theoretical methods
 - Influence of molecular structure
 - Influence of the embedding using multiscale modelling
- Approximation of the electron/energy transfer rates







Singlet fission



SF: spin allowed radiationless process


M. B. Smith, J. Michl, Chem. Rev. 110 (2010), 6891

It is attractive to build the wavefunctions of the solid from state-specific molecular wavefunctions



university of groningen

faculty of science and engineering



stratingh institute for chemistry

Singlet fission rate

Fermi Golden rule in diabatic representation (Marcus theory)

$$k_{SF} \propto \left| \left\langle \Psi_f \middle| H \middle| \Psi_i \right\rangle \right|^2 = \left| \left\langle S_0 S_1 \middle| H \middle| {}^1 TT \right\rangle \right|^2$$

- Electronic coupling between diabatic states
 - Directly accessible with our non orthogonal CI approach
- Adiabatic representation: Non-adiabatic couplings (Landau-Zener model)


$$\langle \Psi_f | \frac{\partial}{\partial Q} | \Psi_i \rangle$$

Potential energy surfaces and conical intersections/
 crossings
 P.F. Barbara, T.J. Mever, M.A. Ratner, J. Phys. Chem. 100 (1996)

P.F. Barbara, T.J. Meyer, M.A. Ratner, *J. Phys. Chem.* **100** (1996), 13148 F. Bernardi, M. Olivucci, and M.A. Robb, *Chem. Soc. Rev.* **25** (1996), 321




Cluster approximation for solids



- Describe solid in terms of molecular wavefunctions
- Compute wavefunctions of each molecule for specific states (CASSCF)
- Form many-electron basis functions (S₀S₀, S₀S₁, ¹TT, CT), each describing a particular combination of molecular states






Non orthogonal configuration interaction

- Describe wavefunctions of a cluster of molecules in terms of (localised) molecular many-electron basis functions (MEBF)
 - MEBFs are spin-adapted antisymmetrised products of molecular wavefunctions:

$$\Phi_{AB}^{KL} = A(\Phi_A^K \times \Phi_B^L)$$

Molecular wavefunction can be any multiconfigurational wavefunction



 Ψ^0 : Ground state

 Ψ^1 : Singlet excited state

 Ψ^T : Triplet excited state

$$\Phi_{AB}^{00} = A(\Psi_A^0 \times \Psi_B^0)$$

$$\Phi_{AB}^{10} = A(\Psi_A^1 \times \Psi_B^0)$$

$$\Phi_{AB}^{01} = A(\Psi_A^0 \times \Psi_B^1)$$

$$\Phi_{AB}^{TT} = A(\Psi_A^T \times \Psi_B^T)$$
:

В

$$\Psi = c_1 \Phi_{AB}^{00} + c_2 \Phi_{AB}^{10} + c_3 \Phi_{AB}^{01} + c_4 \Phi_{AB}^{TT} + \dots$$




faculty of science and engineering


stratingh institute for chemistry

Non Orthogonal Configuration Interaction

- Wavefunction expanded as: $\Psi = \sum_{i=1}^{N} C_i \Phi_i$ with Φ_i a many-electron basis function ((MEBF) Slater determinant, or combination thereof)
- The orbitals ϕ_j in a MEBF are not orthogonal, making the many-electron MEBFs also not orthogonal: $\left\langle \Phi_i \middle| \Phi_j \right\rangle = S_{ij}$
- The non orthogonality of the orbitals within one MEBF and of the orbitals in a different MEBF complicates the calculation of the required Hamiltonian matrix elements $\langle \Phi_i | H | \Phi_j \rangle$
- Solve $(\mathbf{H} E\mathbf{S})(\mathbf{C}) = 0$ to get energies and Ψ (\mathbf{C}_i 's)









Advantages of this NOCI

- Inclusion of orbital relaxation effects
- Inclusion of (static) correlation effects
- Short wavefunction expansions
- Chemical interpretability
 - Description of system in terms of predefined states



• *Con*: no simple Slater rules for the computation of matrix elements of the Hamilton operator in the MEBF basis






Computational Aspects of our NOCI approach

- Typical number of $\left|\Phi_{AB}^{KL}\right\rangle \sim 20$
 - H/S matrices contain ~ 210 elements of the type $\left\langle \Phi_{AB}^{\mathit{KL}} \middle| H \middle| \Phi_{AB}^{\mathit{K'L'}} \right\rangle$ and $\left\langle \Phi_{AB}^{\mathit{KL}} \middle| \Phi_{AB}^{\mathit{K'L'}} \right\rangle$
- If $|\Phi_A^K\rangle$ contains ~ 500 determinants, then $|\Phi_A^K\rangle \times |\Phi_B^L\rangle = |\Phi_{AB}^{KL}\rangle \sim 2.5 \cdot 10^5$
- $\langle \Phi_{AB}^{KL} | H | \Phi_{AB}^{K'L'} \rangle = \sum_{i} \sum_{j} c_{i} c_{j} \langle \Delta_{i} | H | \Delta_{j} \rangle$
- Approximately 10^{7} elements $\left<\Delta_i\middle|H\middle|\Delta_j\right>$ have to be calculated for one matrix element $\left<\Phi_{AB}^{KL}\middle|H\middle|\Phi_{AB}^{K'L'}\right>$
- Aim for high level of parallelism
- Easy to parallelize





Technical Aspects

• Evaluation of $\left<\Delta_i \middle| H\middle| \Delta_i \right>$ with non orthogonal orbitals

$$- H_{ij} = \sum_{i,j} h_{ij} S^{(i,j)} + \sum_{i < k} \sum_{j < l} [(ij \mid kl) - (ik \mid jl)] S^{(i,j,k,l)}$$

- First and second order co-factors needed
- With corresponding orbitals, then $\left\langle c_i \middle| d_j \right\rangle = \lambda_i \delta_{ij}$ and $S^{(i,i)} = \prod_{m \neq i} \lambda_m \quad (S^{(i,j)} = 0 \text{ for } i \neq j)$
- No 4-index, but transform co-factors to common basis in which the corresponding orbitals c_i and d_i are expressed
- SVD and matrix multiplications
- Use GPUs




The GronOR code




- In collaboration with OLCF, based on the GNOME code
 - OpenACC for GPU off-loading
 - Master-worker model with task based load balancing
 - MPI parallelization with point-to-point non-blocking communication
 - Avoid global synchronization and global reduction operations
 - Fault resilient implementation





GronOR Master-Worker Process Layout



Each process group has the same number of worker processes

Each process group should have sufficient aggregate memory to hold all integrals:

One-electron integrals are duplicated


Two-electron integrals are distributed


Consequences of Node Faults: All processes on a failing node fail

If a worker process fails, the entire group to

which it belongs will fail








Case study I - Naphthalene dimer

Anti-symmetrised products of CAS(4,4) wavefunctions



- Neglect of dynamical correlation (S₁ too high)
- Endoergic




faculty of science and engineering

stratingh institute for chemistry


Performance of GronOR


Benchmark run on Summit, requiring 112,867,800 matrix element evaluations

- Each node with 6 MPI ranks
- 1 GPU per rank
- Good scalability with number of nodes
- Performance improvement from GPU is 6.8x










Reduction of required 2-e integrals

- The MOs in the CASSCF wavefunction are expressed in N AOs
 - # 2-e⁻ integrals ~ $N^4/8$
- The n inactive + active MOs of all states of a molecule form a basis as well:


$$\left\{\phi_{1}^{S_{0}},...,\phi_{n}^{S_{0}},\phi_{1}^{S_{1}},...,\phi_{n}^{S_{1}}\right\}$$

- Redundant basis, eliminate linear dependencies, based on threshold ϵ , and transform MOs and 2-e⁻ integrals to new basis
- Dimension of new basis m << N

Case study II - Pyridine



CI threshold – remove contributions from configurations with small CI coefficients




university of groningen


faculty of science and engineering

stratingh institute for chemistry

Singlet fission in tetracene


- Geometry dependence of coupling in solid
 - MD using DFTB (NVT)
 - Estimate coupling using DFT and NOCI








Effective coupling, DFT and NOCI





- Coupling heavily dependent on geometry
- AB/AC orientation best



Tetracene coupling

Large electronic coupling in the AB orientation

Molecules A and B get closer


 Larger HOMO/HOMO and LUMO/LUMO overlap


 Strong mixing of CT states (30%) in local excited state on A and in ¹TT state


Direct coupling: 5 meV

CT mediated coupling: 32 meV










Correlation NOCI vs DFT



Only weak correlation







Conclusions and outlook

- Parallel NOCI program GronOR is working and ready to be used for interesting applications
 - Further optimizations are in progress
 - Better handling of CI lists
 - Inclusion of dynamical correlation and embedding effects
- Tetracene
 - CT states enhance the coupling
 - Coupling and CT state mixing heavily dependent on geometry
 - Static picture not always sufficient for predicting singlet fission
 - Weak correlation NOCI vs DFT couplings
- Further studies:
 - Cibalackrot and other SF molecules
 - Effects of functional groups on electronic coupling







Theoretical Chemistry Group

























stratingh institute for chemistry






Financial support

- OLCF for computer time on SUMMIT (ESP)
- FOM Focus Group 'Next Generation Organic Photovoltaics' (DIFFER)




- FOM/Shell
- ITN-EJD-TCCM (Horizon2020)




















university of groningen

faculty of science and engineering

stratingh institute for chemistry